

# PAPERMINT

## TECHNICAL SHEET

Uptade 09/10/2018

### LINEN

#### SUPPORT - TECHNICAL DATA

HESSIAN - 100% LIN - 144 cms - 305 gr/M<sup>2</sup>

CONSTRUCTION			
	Chaine/ Warp	Trame/ Weft	
Nb thread/ cm	<b>11</b>	<b>12</b>	
Metric thread (Nm)	<b>7,25</b>	<b>7,25</b>	
Average yarn number	<b>7,54</b>		
Tear (N)	<b>22</b>	<b>23</b>	
Rupture (N/cm)	<b>106</b>	<b>37</b>	
	Cycles	Abrasion	Pilling
Martindale	<b>12 500</b>	<b>4</b>	<b>W2 (3/4)</b>

#### MANUFACTURE

Support: **LIN MARCO (WHITE)**

Process: **INR:AS**

1. 21. Impression numérique/ Imp°num. ReNOIR 150 cm
2. 60. SIL Softener Finish.

#### MAINTENANCE

Machine wash 40°C

No chlorine or bleach

Drying machine average temperature

Ironing max. 150°C

No dry cleaning

#### TESTS ET STANDARDS

Light fastness: 4/5 - Norme ISO 105 B02

Abrasion Martindale: 4 - Norme ISO 12947

Rupture, tensile strength: Norme ISO 13935

Tear primed: Norme ISO 13937

#### • Le showroom PaperMint •

36, Rue Pierre Sépard 75009 Paris · France ·

+33 9 87 01 56 95

commande@paper-mint.fr – paper-mint.fr

Instagram : @papermint\_paris – Facebook : /papermintparis